



检测报告

TEST REPORT

委托单位: 邦威科学技术有限公司
Customer: BOIS Technology Ltd
样品名称: CT触媒
Sample Name: CT Catalyst
受检样品数量: 1
Quantity Received:
样品批号: _____
Sample Lot No./Batch No:

报告编号: 2007002281-1
Report No.:
接样日期: 2007年4月20日
Sample Receiving Date:
检测日期: 4月20日 至 5月22日
Testing Period:
签发日期: 2007年5月23日
Date for Reporting:

分析检测结果

Test Results

分析项目 Item	送检处理条件 Deal with Term	含量 (mg/m ³) Amount	实验条件下去除率 (%)Rate of decline under the test condition	检测方法 Method
苯 Benzene	放入样品0min浓度 (mg/m ³)0min after the sample was put in	9.00	—————	GC/MS外标法(JY/T 003-1996) GC/MS external standard method(JY/T 003- 1996)
	放入样品24h浓度 (mg/m ³)24h after the sample was put in	2.28	74.7	
	放入样品72h浓度 (mg/m ³)72h after the sample was put in	0.31	96.6	
(以下空白) (End of Report)				
备 注 Note	在60L的密闭玻璃箱中加入一定量的苯，放入样品(20cm×30cm×2)，暗室处理24小时和72小时，测定苯浓度变化。 A definite volume of benzene was injected into a 60L of airtight glass case,and the sample was put into the case away from light for 24hours and 72hours.The changes of component volume were measured .			
声 明 Declaration	(1)未经本中心的书面批准不得部分复制本报告（全部复制除外）。 The report shall not be reproduced except in full,without the written approval of the laboratory. (2)本报告为委托检验报告，只对来样负责。 The results relate only to the items tested.			

编审: 廖耀承
Organizer and Checker:
职务: 工程师
Business: Engineer

批准: 何建强
Technique Controller:
职务: 高级工程师
Business: Senior Engineer

盖章:
Official Seal:



中国广州分析测试中心

China National Analytical Center, Guangzhou



检测报告

TEST REPORT

委托单位: 邦威科学技术有限公司
Customer: BOIS Technology Ltd
样品名称: CT触媒
Sample Name: CT Catalyst
受检样品数量: 1
Quantity Received:
样品批号: _____
Sample Lot No./Batch No:

报告编号: 2007002281-2
Report No.:
接样日期: 2007年4月20日
Sample Receiving Date:
检测日期: 4月20日 至 5月22日
Testing Period:
签发日期: 2007年5月23日
Date for Reporting:

分析检测结果

Test Results

分析项目 Item	送检处理条件 Deal with Term	含量 (mg/m ³) Amount	实验条件下去除率 (%)Rate of decline under the test condition	检测方法 Method
甲苯 Toluene	放入样品0min浓度 (mg/m ³)0min after the sample was put in	9.00	—————	GC/MS外标法(JY/T 003-1996) GC/MS external standard method(JY/T 003- 1996)
	放入样品24h浓度 (mg/m ³)24h after the sample was put in	3.70	58.9	
	放入样品72h浓度 (mg/m ³)72h after the sample was put in	0.69	92.4	
(以下空白) (End of Report)				
备 注 Note	在60L的密闭玻璃箱中加入一定量的甲苯，放入样品(20cm×30cm×2)，暗室处理24小时和72小时，测定甲苯浓度变化。 A definite volume of Toluene was injected into a 60L of airtight glass case,and the sample was put into the case away from light for 24hours and 72hours,The changes of component volume were measured .			
声 明 Declaration	(1)未经本中心的书面批准不得部分复制本报告（全部复制除外）。 The report shall not be reproduced except in full,without the written approval of the laboratory. (2)本报告为委托检验报告，只对来样负责。 The results relate only to the items tested.			

编审: 廖耀承
Organizer and Checker:
职务: 工程师
Business: Engineer

批准: 何建强
Technique Controller:
职务: 高级工程师
Business: Senior Engineer

盖章: 分析测试中心
Official Seal: (1)



检测报告

TEST REPORT

委托单位: 邦威科学技术有限公司
Customer: BOIS Technology Ltd
样品名称: CT触媒
Sample Name: CT Catalyst
受检样品数量: 1
Quantity Received:
样品批号: _____
Sample Lot No./Batch No:

报告编号: 2007002281-3
Report No.:
接样日期: 2007年4月20日
Sample Receiving Date:
检测日期: 4月20日 至 5月22日
Testing Period:
签发日期: 2007年5月23日
Date for Reporting:

分析检测结果

Test Results

分析项目 Item	送检处理条件 Deal with Term	含量 (mg/m ³) Amount	实验条件下去除率 (%)Rate of decline under the test condition	检测方法 Method
二甲苯 Xylene	放入样品0min浓度 (mg/m ³)0min after the sample was put in	9.00	—————	GC/MS外标法(JY/T 003-1996) GC/MS external standard method(JY/T 003- 1996)
	放入样品24h浓度 (mg/m ³)24h after the sample was put in	1.73	80.8	
	放入样品72h浓度 (mg/m ³)72h after the sample was put in	0.69	92.3	
(以下空白) (End of Report)				
备 注 Note	在60L封闭玻璃箱中加入一定量的二甲苯，放入样品(20cm×30cm×2)，暗室处理24小时和72小时，测定二甲苯浓度变化。 A definite volume of Xylene was injected into a 60L of airtight glass case,and the sample was put into the case away from light for 24hours and 72hours.The changes of component volume were measured .			
声明 Declaration	(1)未经本中心的书面批准不得部分复制本报告（全部复制除外）。 The report shall not be reproduced except in full,without the written approval of the laboratory. (2)本报告为委托检验报告，只对来样负责。 The results relate only to the items tested.			

编审: 廖耀承
Organizer and Checker:
职务: 工程师
Business: Engineer

批准: 何建强
Technique Controller:
职务: 高级工程师
Business: Senior Engineer

盖章: 邦威科学技术有限公司
Official Seal: 分析报告专用章
(1)



检测报告

TEST REPORT

委托单位: 邦威科学技术有限公司
Customer: BOIS Technology Ltd
样品名称: CT触媒
Sample Name: CT Catalyst
受检样品数量: 1
Quantity Received:
样品批号: _____
Sample Lot No./Batch No:

报告编号: 2007002281-4
Report No.:
接样日期: 2007年4月20日
Sample Receiving Date:
检测日期: 4月20日 至 5月22日
Testing Period:
签发日期: 2007年5月23日
Date for Reporting:

分析检测结果

Test Results

分析项目 Item	送检处理条件 Deal with Term	含量 (mg/m ³) Amount	实验条件下去除率 (%)Rate of decline under the test condition	检测方法 Method
苯乙烯 Styrene	放入样品0min浓度 (mg/m ³)0min after the sample was put in	9.00	—————	GC/MS外标法(JY/T 003-1996) GC/MS external standard method(JY/T 003- 1996)
	放入样品24h浓度 (mg/m ³)24h after the sample was put in	1.10	87.7	
	放入样品72h浓度 (mg/m ³)72h after the sample was put in	0.62	93.1	
(以下空白) (End of Report)				
备 注 Note	在60L封闭玻璃箱中加入一定量的苯乙烯，放入样品(20cm×30cm×2)，暗室处理24小时和72小时，测定苯乙烯浓度变化。 A definite volume of Styrene was injected into a 60L of airtight glass case,and the sample was put into the case away from light for 24hours and 72hours.The changes of component volume were measured .			
声明 Declaration	(1)未经本中心的书面批准不得部分复制本报告（全部复制除外）。 The report shall not be reproduced except in full,without the written approval of the laboratory. (2)本报告为委托检验报告，只对来样负责。 The results relate only to the items tested.			

编审: 廖耀承
Organizer and Checker:
职务: 工程师
Business: Engineer

批准: 何建强
Technique Controller:
职务: 高级工程师
Business: Senior Engineer

盖章: _____
Official Seal:





中国广州分析测试中心

China National Analytical Center, Guangzhou



检测报告

TEST REPORT

委托单位: 邦威科学技术有限公司
Customer: BOIS Technology Ltd
样品名称: CT触媒
Sample Name: CT Catalyst
受检样品数量: 1
Quantity Received:
样品批号: _____
Sample Lot No./Batch No.:

报告编号: 2007002281-5
Report No.:
接样日期: 2007年4月20日
Sample Receiving Date:
检测日期: 4月20日 至 5月22日
Testing Period:
签发日期: 2007年5月23日
Date for Reporting:

分析检测结果

Test Results

分析项目 Item	送检处理条件 Deal with Term	含量 (mg/m ³) Amount	实验条件下去除率 (%)Rate of decline under the test condition	检测方法 Method
三氯甲烷 Chloroform	放入样品0min浓度 (mg/m ³)0min after the sample was put in	9.00	—————	HPLC(JY/T024-1996)
	放入样品24h浓度 (mg/m ³)24h after the sample was put in	5.34	40.7	
	放入样品72h浓度 (mg/m ³)72h after the sample was put in	0.57	93.7	
(以下空白) (End of Report)				
备 注 Note	在60L封闭玻璃箱中加入一定量的三氯甲烷，放入样品(20cm×30cm×2)，暗室处理24小时和72小时，测定三氯甲烷浓度变化。 A definite volume of Chloroform was injected into a 60L of airtight glass case,and the sample was put into the case away from light for 24hours and 72hours.The changes of component volume were measured .			
声 明 Declaration	(1)未经本中心的书面批准不得部分复制本报告（全部复制除外）。 The report shall not be reproduced except in full,without the written approval of the laboratory. (2)本报告为委托检验报告，只对来样负责。 The results relate only to the items tested.			

编审: 廖耀承
Organizer and Checker:
职务: 工程师
Business: Engineer

批准: 何建强
Technique Controller:
职务: 高级工程师
Business: Senior Engineer

盖章:
Official Seal





检测报告

TEST REPORT

委托单位: 邦威科学技术有限公司
Customer: BOIS Technology Ltd
样品名称: CT触媒
Sample Name: CT Catalyst
受检样品数量: 1
Quantity Received:
样品批号: _____
Sample Lot No./Batch No.:

报告编号: 2007002281-6
Report No.:
接样日期: 2007年4月20日
Sample Receiving Date:
检测日期: 4月20日至 5月22日
Testing Period:
签发日期: 2007年5月23日
Date for Reporting:

分析检测结果

Test Results

分析项目 Item	送检处理条件 Deal with Term	含量 (mg/m ³) Amount	实验条件下去除率 (%)Rate of decline under the test condition	检测方法 Method
乙苯 Ethylbenzene	放入样品0min浓度 (mg/m ³)0min after the sample was put in	9.00	_____	HPLC(JY/T024-1996)
	放入样品24h浓度 (mg/m ³)24h after the sample was put in	1.69	81.2	
	放入样品72h浓度 (mg/m ³)72h after the sample was put in	0.63	93.0	
(以下空白) (End of Report)				
备 注 Note	在60L封闭玻璃箱中加入一定量的乙苯，放入样品(20cm×30cm×2)，暗室处理24小时和72小时，测定乙苯浓度变化。 A definite volume of Ethylbenzene was injected into a 60L of airtight glass case,and the sample was put into the case away from light for 24hours and 72hours.The changes of component volume were measured .			
声 明 Declaration	(1)未经本中心的书面批准不得部分复制本报告（全部复制除外）。 The report shall not be reproduced except in full,without the written approval of the laboratory (2)本报告为委托检验报告，只对来样负责。 The results relate only to the items tested.			

编审: 廖耀承
Organizer and Checker:
职务: 工程师
Business: Engineer

批准: 何建强
Technique Controller:
职务: 高级工程师
Business: Senior Engineer

盖章:
Official Seal:





中国广州分析测试中心

China National Analytical Center, Guangzhou



检测报告

TEST REPORT

委托单位: 邦威科学技术有限公司
Customer: BOIS Technology Ltd
样品名称: CT触媒
Sample Name: CT Catalyst
受检样品数量: 1
Quantity Received:
样品批号: _____
Sample Lot No./Batch No:

报告编号: 2007002281-7
Report No.:
接样日期: 2007年4月20日
Sample Receiving Date:
检测日期: 4月20日 至 5月22日
Testing Period:
签发日期: 2007年5月23日
Date for Reporting:

分析检测结果

Test Results

分析项目 Item	送检处理条件 Deal with Term	含量 (mg/m ³) Amount	实验条件下去除率 (%)Rate of decline under the test condition	检测方法 Method
四氯乙烯 Tetrachloroethylene	放入样品0min浓度 (mg/m ³)0min after the sample was put in	9.00	—————	HPLC(US EPATO-5)
	放入样品24h浓度 (mg/m ³)24h after the sample was put in	3.59	60.2	
	放入样品72h浓度 (mg/m ³)72h after the sample was put in	2.85	68.2	
(以下空白) (End of Report)				
备 注 Note	在60L封闭玻璃箱中加入一定量的四氯乙烯，放入样品(20cm×30cm×2)，暗室处理24小时和72小时，测定四氯乙烯浓度变化。 A definite volume of Tetrachlorotehylene was injected into a 60L of airtight glass case,and the sample was put into the case away from light for 24hours and 72hours.The changes of component volume were measured .			
声 明 Declaration	(1)未经本中心的书面批准不得部分复制本报告（全部复制除外）。 The report shall not be reproduced except in full,without the written approval of the laboratory. (2)本报告为委托检验报告，只对来样负责。 The results relate only to the items tested.			

编审: 廖耀承
Organizer and Checker:
职务: 工程师
Business: Engineer

批准: 何建强
Technique Controller:
职务: 高级工程师
Business: Senior Engineer

盖章:
Official Seal:





中国广州分析测试中心

China National Analytical Center, Guangzhou



检测报告

TEST REPORT

委托单位: 邦威科学技术有限公司
Customer: BOIS Technology Ltd
样品名称: CT触媒
Sample Name: CT Catalyst
受检样品数量: 1
Quantity Received:
样品批号: _____
Sample Lot No./Batch No:

报告编号: 2007002281-8
Report No.:
接样日期: 2007年4月20日
Sample Receiving Date:
检测日期: 4月20日 至 5月22日
Testing Period:
签发日期: 2007年5月23日
Date for Reporting:

分析检测结果

Test Results

分析项目 Item	送检处理条件 Deal with Term	含量 (mg/m ³) Amount	实验条件下去除率 (%)Rate of decline under the test condition	检测方法 Method
二氧六环 Dioxane	放入样品0min浓度 (mg/m ³)0min after the sample was put in	9.00	_____	GC/MS(JY/T003-1996)
	放入样品24h浓度 (mg/m ³)24h after the sample was put in	2.11	76.5	
	放入样品72h浓度 (mg/m ³)72h after the sample was put in	0.81	91.0	
(以下空白) (End of Report)				
备 注 Note	在60L封闭玻璃箱中加入一定量的二氧六环，放入样品(20cm×30cm×2)，暗室处理24小时和72小时，测定二氧六环浓度变化。 A definite volume of Dioxane was injected into a 60L of airtight glass case,and the sample was put into the case away from light for 24hours and 72hours.The changes of component volume were measured .			
声 明 Declaration	(1)未经本中心的书面批准不得部分复制本报告（全部复制除外）。 The report shall not be reproduced except in full,without the written approval of the laboratory. (2)本报告为委托检验报告，只对来样负责。 The results relate only to the items tested.			

编审: 廖耀承
Organizer and Checker:
职务: 工程师
Business: Engineer

批准: 何建强
Technique Controller:
职务: 高级工程师
Business: Senior Engineer

盖章: _____
Official Seal:

